



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61K 49/00	A1	(11) International Publication Number: WO 96/18420 (43) International Publication Date: 20 June 1996 (20.06.96)
---	----	--

(21) International Application Number: PCT/IB95/01124

(22) International Filing Date: 14 December 1995 (14.12.95)

(30) Priority Data:

94810731.3 16 December 1994 (16.12.94) EP

(34) Countries for which the regional or
international application was filed: CH et al.(71) Applicant: BRACCO RESEARCH S.A. [CH/CH]; 7, route de
Drize, CH-1227 Carouge (CH).(72) Inventors: YAN, Feng; 12, route des Acacias, CH-1227
Genève (CH). SCHNEIDER, Michel; 34, route d'Annecy,
CH-1256 Troinex (CH). BROCHOT, Jean; L'Agnellu, F-
74160 Feigères (FR).(74) Agent: TOMOV-GRISOGONO, Nenad; Bracco Research S.A.,
7, route de Drize, CH-1227 Carouge (CH).(81) Designated States: AU, CA, CN, CZ, FI, HU, IS, JP, KR, MX,
NO, NZ, PL, RU, UA, European patent (AT, BE, CH, DE,
DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published

With international search report.

(54) Title: METHOD OF STORAGE OF ULTRASONIC GAS SUSPENSIONS

(57) Abstract

Disclosed are suspensions of gas microbubbles immobilised within a frozen aqueous carrier liquid comprising usual additives and stabilisers, in which the carrier liquid is physiologically acceptable, the immobilised gas microbubbles are microbubbles bound by an evanescent envelope or a tangible membrane. The suspensions, when in liquid form, are injectable and useful as a contrast agent in ultrasonic imaging of blood pool and tissue of living beings. The gas microbubbles are immobilised within the carrier by freezing a suspension of microbubbles with average sizes below 50 μm , preferably below 10 μm and more preferably between 2 μm and 8 μm , to a temperature between -1 °C and -76 °C and maintaining this temperature for prolonged periods of time. The microbubbles may be stabilised by a surfactant such as a lamellar phospholipid or may comprise a membrane made of synthetic or natural polymer or protein. A method of cold storage of microbubble suspensions as well as their use is also disclosed.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TC	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

METHOD OF STORAGE OF ULTRASONIC GAS SUSPENSIONS

Technical Field

The invention relates to suspensions of gas bubbles immobilised within a frozen aqueous carrier medium. The invention also concerns a
5 method of cold storage of the gas bubble suspensions and their use as contrast agents for ultrasonic imaging of human and animal body.

Background Art

10 Rapid development of ultrasound contrast agents in the recent years has generated a number of different formulations which are useful in ultrasound imaging of organs and tissue of human or animal body. These agents are designed to be used primarily as intravenous or intra-arterial
15 injectables in conjunction with the use of medical echographic equipment. These instruments typically group B-mode image formation (based on the spatial distribution of backscatter tissue properties) and Doppler signal processing (based on Continuous Wave or pulsed Doppler processing of ultrasonic echoes to determine blood or liquid flow parameters). Other
20 ultrasound imaging methods could also benefit from these agents in the future, such as Ultrasound Computed Tomography (measuring attenuation in transmission), or Diffraction Computed Tomography (measuring scattering and attenuation parameters in angular reflection). Based on suspensions of gas microbubbles in aqueous liquid carriers, these
25 injectable formulations may basically be divided into two categories: Aqueous suspensions in which the gas microbubbles are bounded by the gas/liquid interface, or an evanescent envelope involving the molecules of the liquid and a surfactant loosely bound at the gas to liquid interface and suspensions in which the microbubbles have a material boundary or a
30 tangible envelope formed of natural or synthetic polymers. In the latter case the microbubbles are referred to as microballoons. There is yet another kind of ultrasound contrast agents: suspensions of porous particles of polymers or other solids which carry gas microbubbles entrapped within the pores of the microparticles. These contrast agents
35 are considered here as a variant of the microballoon kind. Although

physically different, both kinds of gas microbubbles when in suspension are useful as ultrasonic contrast agents. More on these different formulations may be found in EP-A-0 077 752 (Schering), EP-A-0 123 235 (Schering), EP-A-0 324 938 (Widder et al.), EP-A-0 474 833 (Schneider et al.),
5 EP-A-0 458 745 (Bichon et al.), US-A-4,900,540 (Ryan), US-A-5,230,882 (Unger), etc.

Certain of the above mentioned ultrasound contrast agents are developed and commercially available, while others are at different stages
10 of clinical trials. However, whether commercially available or on clinical tests, these products all suffer from problems linked with storage. The problems of storage are intrinsic to suspensions which, due to their very nature, undergo phase separation or segregation, gas bubble aggregation,
15 gas diffusion and, after long periods, even precipitation of various additives. Segregation of the gas microbubbles or microballoons comes from the fact that the suspensions are typically made of uncalibrated microbubbles whose sizes vary from about 1 μm up to about 50 μm . A vast
majority of the gas bubbles in the known suspensions is found to be between 1 μm and about 10 μm . Due to the microbubble size distribution,
20 these suspensions, during storage, undergo segregation in which larger microbubbles migrate to the top while the smaller ones concentrate in the lower parts, often leading to complete phase separation. Attempts to resolve this problem through the use of viscosity enhancing agents have shown that the rate of segregation may be reduced but not eliminated.

25 Gas microbubble aggregation is a process during which the larger bubbles absorb the smaller ones, thus growing in size. With phase separation, this process accelerates and suspensions with microbubbles having average size of e.g. between 2 μm and 8 μm after a while may
30 evolve in suspensions with microbubble size between e.g. 5 μm to 12 μm or larger. This is particularly undesirable in cases where suspensions of calibrated microbubbles and suspensions intended for opacification of the left heart are concerned. The change in size does not only alter the echogenic properties of the contrast agent, but also renders the agent
35 inapplicable for certain applications such as those based on the passage of the microbubbles through the lungs. Microbubbles with sizes over 10 μm are unlikely to pass through the lung capillaries and therefore, in addition

to creating hazardous conditions such suspensions are less suitable for imaging of the left heart.

Another problem with gas suspensions and their storage comes
5 from the gas diffusion which occurs at relatively low rates, but which accelerates with phase separation. Inevitable escape of the gas from the microbubble suspensions is thus further aggravated and in extreme cases may lead to complete gas depletion of the medium. Hence, the combined effect of these various mechanisms on destruction of the gas suspensions
10 therefore results in a very rapid degradation of the agent.

In some ultrasound imaging approaches, one of the desirable aspects of these contrast agents is for the microbubbles or gas-containing particles to be distributed within a tight size window. The reason is given hereafter.
15 The effectiveness of these agents to increase the contrast in images produced by medical ultrasonographic equipment is based, primarily, on greatly enhanced scattering of the incoming ultrasonic energy, and secondly, on modified attenuation properties of the tissues containing these agents. By contrast, it is meant a measure of the relative signal
20 amplitude obtained from regions to be perfused by the contrast agent compared with the signal amplitude from regions not receiving the contrast agent. By enhancement, it is meant an increase in the contrast value observed following administration of the contrast agent, compared to the contrast observed prior administration. As mentioned earlier, the
25 type of imaging equipment most directly benefitting from these agents is the family of echographic instruments (B-mode or Doppler). The different attenuation properties of tissues containing the agent compared to those not containing the agent can also be exploited to improve the diagnostic value of the imaging procedure. Furthermore, the ultrasonic-frequency
30 dependence of both the scattering and attenuation properties of the agent can be exploited to increase spatial tissue discrimination further. In these cases, the physical laws governing this frequency dependence systematically depend on the microbubble- or particle-size. Thus, the algorithms used are more efficient when acting on echoes originating
35 from microbubbles or particles with tight size-distribution. As an example, one such approach exploits non-linear oscillation of microbubbles to detect echo frequency-components at the second-harmonic of the fundamental excitation frequency. Since the tissues not containing the contrast agent do

not exhibit the same non-linear behaviour as the microbubbles, this method is able to enhance significantly the contrast between the regions containing and those not containing the contrast agent. This enhancement is more pronounced, for a given particle-count per unit volume, when the sizes are narrowly distributed. However, the preparation of products with such narrow-size distributions is time consuming; providing a ready supply of these calibrated suspensions would facilitate greatly the further development and use of this technique. Reliable storage of such preparations with unchanged size distributions is thus also of great interest.

Further difficulties with storage of aqueous gas suspensions is experienced with ultrasound contrast agents which contain phospholipids as stabilisers of the gas microbubbles. Due to hydrolysis of phospholipids, the concentration of the stabilizer (surfactant), during storage, is constantly diminished, causing loss of the microbubble content and degradation of echogenic properties of the suspension. Thus so far the problem of storage of ultrasound contrast agents comprising gas microbubble suspensions remains open.

Cold storage of aqueous gas suspensions by freezing has been known for quite some time in the food industry. For example, US-A-4,347,707 (General Foods Corp.) discloses storage of gasified ice with high gas content and good storage stability by a method in which the gasified ice is prepared by contacting an aqueous liquid with hydrate-forming gases under pressure and at a temperature such that the gas hydrate complex suspended in the liquid is formed and the temperature and pressure are controllably lowered to produce e.g. carbonated ice with 85-110 ml of CO₂/g. According to the document, the gasified ice has high gas content, prolonged storage stability, is suitable for commercial distribution in the frozen state and, when placed in water, provides vigorous effervescence.

It follows that freezing of the gas suspensions in order to store them for prolonged periods of time, and reuse the preserved suspensions when necessary would not be suitable for ultrasonic contrast agents because the suspended gas has a tendency to escape from the carrier medium during defrosting. Further difficulty with the frozen gas suspensions of microbubbles lies in the fact that the expansion of the carrier medium

during the freezing creates internal forces which simply destroy or crush the microbubble envelope liberating the entrapped gas and letting it escape either during storage or later during defrosting of the suspension. This problem is particularly severe for the suspensions of microbubbles having material or tangible envelopes.

Summary of the Invention

Briefly summarised, the invention relates to frozen suspensions of gas bubbles immobilised within a frozen aqueous carrier medium in which the carrier medium comprising the gas bubbles with usual additives is a physiologically acceptable carrier. The immobilised gas bubbles are microbubbles bound by an evanescent envelope or a tangible membrane and the suspensions, when in liquid form, are injectable into living beings and are useful as a contrast agents for ultrasonic imaging of the blood pool and tissue of human and animal patients.

According to the invention, the temperatures of the frozen suspensions are between -1°C and -196°C , preferably between -10°C and -76°C while the size of the gas microbubbles is below $50\text{ }\mu\text{m}$ and preferably below $10\text{ }\mu\text{m}$. Particularly useful are suspensions in which the size of the microbubbles is between $2\text{ }\mu\text{m}$ and $9\text{ }\mu\text{m}$, while the suspensions of microbubbles with size between $3\text{ }\mu\text{m}$ and $5\text{ }\mu\text{m}$ are even more useful.

In view of the difference in biodegradability between the suspensions comprising gas microballoons or microbubbles with a tangible envelope in which the membrane is made of synthetic or natural polymer or protein, and the suspensions comprising gas microbubbles with evanescent envelopes, the frozen suspensions of the latter would be more advantageous, particularly when lamellar phospholipids in the form of mono- or pluri-molecular membrane layers are used.

The invention also relates to a method of storing microbubble suspensions in which the suspension is placed into a cooling device, microbubbles are immobilised within the carrier medium by cooling to a temperature below the freezing point of the suspension, preferably a temperature between -1°C and -196°C , and more preferably between -10°C

and -76°C , and the freezing conditions are maintained for prolonged periods of time. Optionally, the frozen suspension may be kept in an atmosphere of an inert gas or a mixture of gases, at least one of which is the gas encapsulated in the microbubbles. The gas is preferably selected from halogen containing gases, air, oxygen, nitrogen, carbon dioxide or mixtures thereof.

Use of injectable suspensions of the invention for ultrasonic echography imaging of organs and tissue and the manufacture of ultrasound contrast agents is also disclosed.

Brief Description of the Drawings

Figure 1 is a plot of change in the bubble concentration (count) in defrosted suspensions of SF_6 and air containing 5% of C_5F_{12} microbubbles in an aqueous carrier medium as a function of storage temperature.

Figure 2 is a plot of change in the total gas volume of defrosted suspensions of SF_6 and air containing 5% C_5F_{12} microbubbles in an aqueous carrier medium as a function of storage temperature.

Figure 3 is a graphical presentation of change in absorbance of defrosted microbubble suspensions as a function of external pressure applied and storage temperature.

Figure 4 is a diagram showing change of relative absorbance as a function of external pressure applied to defrosted suspensions after storage at different temperatures.

Figure 5 is a diagram showing the microbubble size distribution in number (Fig. 5A) and gas volume (Fig. 5B) of calibrated microbubbles with average size of $3\text{ }\mu\text{m}$, $4\text{ }\mu\text{m}$ and $6\text{ }\mu\text{m}$.

Figure 6 is a diagram showing the microbubble size distribution in number (Fig. 6A) and gas volume (Fig. 6B) for a sample of non-calibrated microbubbles.

Detailed Description of the Invention

According to the invention, there is provided a frozen suspension of gas microbubbles in which the microbubbles are immobilised within a frozen aqueous carrier medium which in addition to the microbubbles includes usual additives. The aqueous carrier is physiologically acceptable and the suspension, when in a liquid form is injectable into living beings and is useful as an ultrasound contrast agent for imaging of blood pool and tissue of human and animal patients. The immobilised gas microbubbles bound by an evanescent envelope or a tangible membrane are entrapped between molecules of the frozen carrier medium whose temperature is between -1°C and -196°C , preferably between -10°C and -76°C . The exact temperature range used will depend on the choice of gas in the microbubbles but also on the kind and quantity of additives used. Thus, for example, in the case of air or nitrogen, the temperature may be anywhere between -1°C and -196°C , while, in the case of C_4F_8 , the temperature will be between -1°C and -5°C . When polyoxypropylene/polyoxyethylene copolymers or polyethylene glycol are used as additives depending on the total amount present in the suspension the highest acceptable temperature may be -5°C or even -10°C instead of -1°C .

The size of most of the microbubbles in the suspension is typically below $50\text{ }\mu\text{m}$, but for intravenously injectable contrast agents the microbubble size will be preferably below $10\text{ }\mu\text{m}$.

25

For most applications the suspensions with microbubbles having the size distribution between $2\text{ }\mu\text{m}$ and $9\text{ }\mu\text{m}$ would satisfy the requirements, however, when dealing with suspensions of calibrated microbubbles the sizes may be anywhere in that range. For example, between $2\text{-}4\text{ }\mu\text{m}$, $3\text{-}5\text{ }\mu\text{m}$, $4\text{-}6\text{ }\mu\text{m}$, $5\text{-}7\text{ }\mu\text{m}$, $6\text{-}8\text{ }\mu\text{m}$, $7\text{-}9\text{ }\mu\text{m}$ however the microbubble with the size range between $3\text{ }\mu\text{m}$ and $5\text{ }\mu\text{m}$ is preferred.

30

Thus the invention also provides frozen suspensions of microbubbles with a very narrow size distribution. Typical microbubble size distributions of suspensions of calibrated microbubbles will be as those illustrated in Fig. 5. where the distributions are given in terms of the microbubble number distribution (as determined by Coulter counter) Fig. 5A and in terms of the microbubble volume distribution (as determined

35

by Coulter counter) Fig. 5B. In contrast to suspensions containing calibrated microbubbles, the suspensions containing non-calibrated gas bubbles will have typically the number and the volume size distribution patterns similar to those shown in Figures 6A & 6B. From these figures it is readily appreciated that the echographic responses suspensions made from calibrated gas microbubbles will be more uniform, will provide less scatter and consequently sharper images than the suspensions with non-calibrated microbubbles. As already mentioned these calibrated suspensions are very desirable but their use so far was very limited. Thus these desirable suspensions are now readily available through a simple conversion of frozen suspensions which may be stored at low temperatures for prolonged periods of time without undue loss of their initial echogenicity.

A further advantage of the invention comes from the fact that in order to generate echo-signal components at twice the fundamental frequency, second harmonic imaging requires non-linear oscillation of the contrast agent. Such behaviour imposes the ultrasound excitation level to exceed a certain acoustic threshold at a certain depth in tissue. During non-linear oscillation, a frequency conversion takes place, causing conversion of the acoustic energy from the fundamental excitation frequency up to its second harmonic. Thus significant energies transmitted to the microbubbles during this type of imaging require microbubbles sufficiently resistant to survive these conditions. The invention provides for an easy and convenient access to suspensions of having microbubbles with good resistance to pressure variations as they can now be prepared in advance, stored and used when needed.

As already mentioned, in addition to the gas microbubbles, the frozen suspensions of the invention contain additives which include various surfactants, viscosity enhancing agents, stabilisers, etc. Surfactants which may include film forming and non-film forming surfactants include phospholipids in lamellar or laminar form which are known to stabilise the microbubble evanescent gas/liquid envelope. The lamellar phospholipids may be in the form of mono- or pluri-molecular membrane layers or liposomes.

Depending on the type of microbubbles, i.e. with evanescent envelope or a tangible membrane the carrier medium may include as additives hydrating agents and/or hydrophilic stabiliser compounds such as polyethylene glycol, carbohydrates such as galactose, lactose or sucrose, dextran, starch, and other polysaccharides or other conventional additives like polyoxypropylene glycol and polyoxyethylene glycol and their copolymers; ethers of fatty alcohols with polyoxyalkylene glycols; esters of fatty acids with polyoxyalkylated sorbitan; soaps; glycerol-polyalkylene stearate; glycerol-polyoxyethylene ricinoleate; homo- and copolymers of polyalkylene glycols; polyethoxylated soya-oil and castor oil as well as hydrogenated derivatives; ethers and esters of sucrose or other carbohydrates with fatty acids, fatty alcohols, these being optionally polyoxyalkylated; mono-, di- and triglycerides of saturated or unsaturated fatty acids; glycerides of soya-oil and sucrose may also be used. Surfactants may be film forming and non-film forming and may include polymerizable amphiphilic compounds of the type of linoleyl-lecithins or polyethylene dodecanoate. Preferably, the surfactants are film forming and more preferably are phospholipids selected from phosphatidic acid, phosphatidylcholine, phosphatidylethanolamine, phosphatidylserine, phosphatidylglycerol phosphatidylinositol, cardiolipin, sphingomyelin and mixtures thereof. In addition to the film forming surfactants mentioned, the suspensions may further include up to 50% by weight of non-lamellar surfactants selected from fatty acids, esters and ethers of fatty acids and alcohols with polyols such as polyalkylene glycols, polyalkylenated sugars and other carbohydrates, and polyalkylenated glycerol. Particularly suitable substances include dicetylphosphate, cholesterol, ergosterol, phytosterol, sitosterol, lanosterol, tocopherol, propyl gallate, ascorbyl palmitate and butylated hydroxytoluene.

It is understood that the invention is not limited only to the suspensions of gas microbubbles with an evanescent envelope. Any suitable particles filled with gases such as porous particles, liposomes or microballoons having an envelope produced from phospholipids, synthetic or natural polymers or proteins may conveniently be used. Thus it has been established that microballoons prepared with albumin, or liposome vesicles can be successfully stored for prolonged periods of time in the frozen state. Defrosted suspensions containing these microballoons have demonstrated acceptable echogenicities showing a relatively small

microbubble loss. Suspensions in which the microbubbles were stabilised with sorbitol or non-ionic surfactants such as polyoxyethylene/polyoxypropylene copolymers (commercially known as Pluronic®) have demonstrated equally good imaging capability after storage.

5 The additives used for the suspensions of the invention may further include viscosity enhancers and/or stabilisers selected from linear and cross-linked poly- and oligo-saccharides, sugars, hydrophilic polymers and iodinated compounds. In such case the weight ratio of these
10 compounds to the surfactants comprised is between about 1:5 to 100:1.

 The suspensions according to the invention and prepared with different gases or gas mixtures usually contain 10^7 - 10^8 microbubbles/ml, 10^8 - 10^9 microbubbles/ml or 10^9 - 10^{10} microbubbles/ml. These
15 concentrations remain virtually the same after prolonged storage, i.e. several months, and if suspensions are made with SF₆, C₃F₈ or their mixtures or mixtures of air with SF₆ or C₅F₁₂ they do not change even after repeated freeze and thaw cycles.

20 When the microbubbles in the suspension have a tangible membrane, the membrane is made of synthetic or natural polymer or protein. The polymer which constitutes the envelope or bounding membrane of the injectable microballoons can be selected from most hydrophilic, biodegradable physiologically compatible polymers. Among
25 such polymers one can cite polysaccharides of low water solubility, polylactides and polyglycolides and their copolymers, copolymers of lactides and lactones such as ϵ -caprolactone, δ -valerolactone and polypeptides. The great versatility in the selection of synthetic polymers is here of advantage since, as with allergic patients, one may wish to avoid
30 using microballoons made of natural proteins (albumin, gelatin). Other suitable polymers include poly-(ortho)esters, copolymers of lactic and glycolic acid, poly(DL-lactide-co- δ -caprolactone), poly(DL-lactide-co- δ -valerolactone), poly(DL-lactide-co-g-butyrolactone), polyalkyl-cyanoacrylates; polyamides, polyhydroxybutyrate; polydioxanone; poly- β -aminoketones, polyphosphazenes and polyanhydrides. Polyamino-acids
35 such as polyglutamic and polyaspartic acids can also be used as well as their derivatives, i.e. partial esters with lower alcohols or glycols. One useful example of such polymers is poly-(tert-butylglutamate).

When the membrane is made from proteinaceous material the protein is albumin.

Although in conjunction with suitable surfactants and stabilisers,
5 halogen containing gases, air, oxygen, nitrogen or carbon dioxide may be used alone, recently, use of mixtures of the halogen containing gases with air, oxygen, nitrogen and carbon dioxide has also been proposed. The halogen containing gases are gases selected from sulphur hexafluoride, tetrafluoromethane, chlorotrifluoromethane, dichlorodifluoromethane,
10 bromotrifluoromethane, bromochlorodifluoromethane, dibromodifluoromethane, dichlorotetrafluoroethane, chloropentafluoroethane, hexafluoroethane, hexafluoropropylene, octafluoropropane, hexafluorobutadiene, octafluoro-2-butene, octafluorocyclobutane, decafluorobutane, perfluorocyclopentane, dodecafluoropentane or mixtures of
15 thereof and preferably sulfur hexafluoride, tetrafluoromethane, hexafluoroethane, hexafluoropropylene, octafluoropropane, hexafluorobutadiene, octafluoro-2-butene, octafluorocyclobutane, decafluorobutane, perfluorocyclopentane, dodecafluoropentane.

20 The invention also relates to a method of storing microbubble suspensions in which the suspension is placed into a cooling device such as a refrigerator, microbubbles are immobilised within the carrier medium by cooling to a temperature below the freezing point of the suspension, preferably a temperature between -1°C and -196°C , and more preferably
25 between -10°C and -76°C the freezing conditions are maintained for prolonged periods of time. Optionally, the frozen suspension is kept in an atmosphere of an inert gas or a mixture of gases at least one of which is the gas encapsulated in the microbubbles. The gas is preferably selected from halogen containing gases, air, oxygen, nitrogen, carbon dioxide or
30 mixtures thereof.

It has been established that gases or gas mixtures used for the frozen suspension of the invention should have boiling points which are below -18°C . This means that suspensions made with halogenated gases such as
35 C_4F_8 and C_5F_{10} alone will have very poor storage stability and will lose practically all of their echogenicity after freezing. This was particularly surprising since all other halogenated gases produced very stable frozen suspensions which survived several freeze/thaw cycles without

significant loss of echogenicity. Even "doping" these gases with small amounts of other halogenated gases or even vapours of halogenated substance which at room temperatures are liquids such as C_5F_{12} has produced mixtures which could not be stored frozen. On the other hand, admixing air with certain quantities of these gases have produced suspensions which have had very good storage stability and very good echogenicity after several freeze/thaw cycles.

As mentioned above, when in a liquid state, the injectable suspensions of the invention are useful as contrast agents for ultrasonic imaging of organs and tissue. Clearly, prior to use, the suspensions are defrosted and optionally maintained at room temperature for a period of time and then administered to the patient. The patient is then scanned with an ultrasonic probe and an image of the scanned region is produced.

Also within the scope of the invention is a method of the manufacture of ultrasound echographic contrast agents from the frozen injectable suspensions of the invention. By the manufacture it is meant that fairly concentrated suspensions (e.g. 10^{10} - 10^{11} microbubbles/ml or more) of calibrated or uncalibrated microbubbles are stored in a frozen state for a period of time and when needed defrosted suspensions are, optionally, diluted to the desired concentration by addition of the same or a different physiologically acceptable liquid carrier. It is also envisaged that at this point further additives or conditioners may be added.

The invention is further illustrated by the following examples:

Example 1

Fifty eight milligrams of diarachidoylphosphatidylcholine (DAPC), 2.4 mg of dipalmitoylphosphatidic acid (DPPA) both from Avanti Polar Lipids (USA) and 3.94 g of polyethyleneglycol (PEG 4000 from Siegfried) were dissolved at $60^{\circ}C$ in tert-butanol (20 ml) in a round bottom glass vessel. The clear solution was rapidly cooled at $-45^{\circ}C$ and lyophilised. Aliquots (25 mg) of the white cake obtained were introduced in 10 ml glass vials. The vials were closed with rubber stoppers, evacuated, and filled with selected gases or gas mixtures (see Table 1). Saline (0.9% NaCl) was

then injected through the stoppers (5 ml per vial) and the lyophilisates were dissolved by vigorous shaking.

The microbubble suspensions were introduced in a cold storage room (-18°C). Three days later they were thawed at room temperature (23°C) and analysed with regard to bubble concentration (by using a Coulter Multisizer) and absorbance at 700 nm of a 1/50 dilution. The absorbance at 700 nm is a measure of the overall turbidity of the bubble suspension.

TABLE 1

Gas or gas mixture	Boiling point (°C)	Water solubility*	Absorbance (% of initial)	Bubbles recovered (%)
air	-195	0.0167	33	14
SF ₆	-63.8	0.005	57	23
C ₃ F ₈	-36.7	<<0.005	59	54
C ₄ F ₈	-6	0.016	11	8
C ₄ F ₁₀	-1.7	<0.005	7	4
air (+5% C ₅ F ₁₂)	-195	0.0167	71	49
air (+10% C ₅ F ₁₂)	-195	0.0167	55	34
air (+10% C ₄ F ₈)	-195	0.0167	50	30
air (+10% C ₄ F ₁₀)	-195	0.016	52	32
SF ₆ (+5% C ₅ F ₁₂)	-63.8	0.005	62	41
C ₃ F ₈ (+5% C ₅ F ₁₂)	-36.7	<<0.005	84	71
C ₄ F ₈ (+5% C ₅ F ₁₂)	-6	0.016	7	6
C ₄ F ₁₀ (+5% C ₅ F ₁₂)	-1.7	<0.005	1	1
Xenon (+5% C ₅ F ₁₂)	-108.1	0.108	38	17

* expressed as Bunsen coefficient

Results given in Table 1 show that the stability to freezing depends on the boiling point and the water solubility of the gas. Less bubbles are recovered in the case of gases with boiling points above -18°C. With regard to the gases with boiling points below -18°C, the lower the solubility in water the higher the recovery of bubbles. It is also interesting to note that the addition of a small amount of a high molecular weight gas with low water solubility such as dodecafluoropentane (C₅F₁₂) improves the recovery of bubbles after thawing in the case of gases with low boiling points but not for gases with boiling points above -18°C. Finally,

microbubbles filled with C_4F_8 and C_4F_{10} on their own or in mixtures with small amounts of dodecafluoropentane have very poor stability to freezing/thawing. However, when these gases are used in combination with air suspensions of microbubbles containing the mixtures show better results in terms of echogenicity or the microbubble loss than the suspensions containing air microbubbles.

Example 2

Suspensions of SF_6 microbubbles prepared as described in Example 1 were frozen slowly (approx. 30 min) to $-18^\circ C$ or rapidly (within a minute) to $-45^\circ C$. Other suspensions of SF_6 microbubbles were first kept at room temperature until all bubbles had risen at the surface before freezing. Others were frozen while the bubbles were homogeneously distributed in the solution. The frozen suspensions were stored at $-18^\circ C$ and $-45^\circ C$ for one month and then defrosted.

TABLE 2

Test	Bubble conc. (% of initial)	Bubble volume (% of initial)
Slow freezing ($-18^\circ C$)	16	39
Rapid freezing ($-45^\circ C$)	24	51
Decanted ($-18^\circ C$)	14	34
Homogeneous ($-18^\circ C$)	24	61

The results in Table 2 show that the rate of freezing has a relatively small influence on the final result. The recovery in the case of homogeneous suspensions is better than in the case of suspensions of decanted microbubbles.

Example 3

Multilamellar liposomes (MLVs) were prepared by dissolving 4.5 g of hydrogenated soy phosphatidylcholine (HSPC from Nattermann) and 0.5 g of dicetylphosphate (Fluka, Switzerland) in chloroform-methanol

(2/1), then evaporating the solvents to dryness in a round bottomed flask using a rotary evaporator. The residual lipid film was dried in a vacuum desiccator. After addition of 100 ml of distilled water the suspension was incubated at 70°C for 30 min under agitation. The liposome suspension
 5 was adjusted to a final lipid concentration of 25 mg per ml by addition of distilled water.

An aliquot of the liposome suspension (100 ml) was introduced in a gas tight glass reactor equipped with a high speed mechanical emulsifier
 10 (Polytron). The gas phase in the reactor was air containing 5% C₅F₁₂ (as determined by density measurement). After homogenisation (10'000 rpm, 1 min) the milky suspension obtained was introduced in a decantation funnel. After 6 hours, a white layer of bubbles could be seen on top of the solution. The lower (liposomes containing) phase was removed, a small
 15 amount of fresh water added and the microbubble layer rehomogenised. The procedure (decantation) was repeated and four samples with different microbubble sizes were prepared (see WO94/09829). The samples were frozen at -18°C and 24 hours later thawed to room temperature.

TABLE 3

Initial diameter Dn (µm)	Diameter Dn after freeze/thaw	Bubble conc. (% of initial)	Absorbance 700 nm (% of initial)
2.5	2.5	19	20
4.6	4.5	60	68
6.0	6.2	86	100
7.6	8.1	76	91

20

From the results obtained (Table 3) it seems that the freeze/thaw treatment does not have an influence on the mean microbubble diameter. From the experiments it appears that microbubbles with larger diameter (>2.5 µm) withstand the freeze/thaw treatment better than microbubbles
 25 with smaller diameter. It is further observed that in certain cases the rate of defrosting may influence the final concentration of the microbubbles present in the sample. The exact relationship is still unclear, however, there are indications that the loss of microbubbles is inversely

proportional to the defrosting rate. Preliminary results indicate that better results in terms of microbubble concentration (count) and the total volume of gas in the suspensions are obtained at accelerated defrosting i.e. defrosting carried out in a water bath at 25°C than when the samples are left at 5°C or 20°C to defrost more gradually. The largest loss of gas volume was observed for samples defrosted at 5°C.

Example 4

The experiment described in Example 3 was repeated using a mixture of surfactants instead of MLVs. The surfactant mixture was obtained by dissolving 1 g of dipalmitoylphosphatidylglycerol (DPPG Na salt from Avanti Polar Lipids, USA) and 3 g of Pluronic® F68 (a copolymer of polyoxyethylene-polyoxypropylene with a molecular weight of 8400) in distilled water (80 ml). After heating at about 70°C a clear solution was obtained. This solution was cooled at room temperature and the volume was completed to 100 ml with glycerol. The surfactant solution was introduced in the glass tight reactor equipped with a Polytron emulsifier. After homogenisation (10'000 rpm, 1 min) a milky suspension was obtained with on top a layer of foam. The foam was discarded and the lower phase containing 10^9 microbubbles per ml was recovered. This phase was left for several hours before collecting the white microbubble layer. The microbubbles collected were rehomogenised in distilled water, decanted a second time and frozen/thawed as described previously. When comparing the characteristics of the bubbles before and after freezing, no significant variation in the total bubble concentration (before 1.3×10^8 bubbles per ml, after 1.25×10^8), or the mean diameter D_n (before 4.0 μm , after 3.9) was observed.

Example 5

SF₆ bubbles were prepared as described in Example 1 and decanted as described in Example 3. During the removal of the lower aqueous phase, an equivalent volume of SF₆ gas was introduced in the funnel. The bubble layer was resuspended in distilled water, 0.9% NaCl, 3% aqueous glycerol solution and 100 mg/ml trehalose solution. The bubble concentrations and absorbance at 700 nm (after dilution) was determined prior to and after a freeze-thaw treatment.

The results in Table 4 show an excellent recovery of the bubbles independently of the suspension medium. It is important to note that the microbubble recovery here is between 66 and 96% which may seem in a contradiction with previous results reported in Table 1 & 2. However, in this case, firstly, the microbubbles are calibrated i.e. more stable than uncalibrated ones, and secondly the size of the bubbles used here is above 4 μm .

TABLE 4

Suspension medium	Absorbance 700 nm (% of initial)	Bubble conc. (% of initial)
distilled water	69	66
0.9% NaCl	86	92
3% glycerol	92	96
100 mg/ml trehalose	89	73

Example 6

Decanted SF_6 microbubbles were obtained as described in Example 5. The microbubble layer was suspended at different bubble concentrations in 0.9% NaCl, then frozen at -18°C , stored for about 4 months and thawed at room temperature.

TABLE 5

Bubble concentration ($\times 10^8/\text{ml}$)		Bubble volume ($\mu\text{l}/\text{ml}$)		Bubble diameter (μm)	
native	freeze/thaw	native	freeze/thaw	native	freeze thaw
1.9	1.9 (1.9)*	6.8	6.0 (5.5)*	3.1	3.0 (2.9)*
3.9	3.7 (3.3)	14.7	11.5 (9.4)	3.1	2.8 (2.6)
5.9	5.7 (5.4)	22.6	20.4 (18.6)	3.1	3.0 (3.0)
7.7	7.6 (6.1)	28.3	24.6 (17.0)	3.0	2.9 (2.7)

* in parenthesis, results obtained after a second freeze/thaw treatment

The results gathered in Table 5 show no significant effect of the bubble concentration on the resistance to freeze/thaw. Even a second freeze/thaw treatment which was performed after the storage did not effect the final concentration, showing that these suspensions are resistant to repeated freeze and thaw cycles even after storage without great loss in the bubble count and damage to the echogenicity of the samples.

Example 7

Sonicated albumin microspheres were prepared using the method described in EP-A-0 324 928 (Widder). Briefly, 5 ml of a sterile 5% human albumin solution (from the Blood Transfusion Service of the Swiss Red Cross, Bern Switzerland) were introduced in a 10 ml calibrated syringe. A sonicator probe (Model 250 from Branson Ultrasonic Corp. USA) was lowered into the solution down to the 4 ml mark. Sonication was carried out for 30 sec at an energy setting of 7. Then the sonicator probe was raised up to the 6 ml mark (i.e. above the solution level) and sonication was pursued in the pulse mode (0.3 s/cycle) for 40 seconds. After removal of a foam layer, a suspension of albumin microspheres was obtained containing 1.5×10^8 bubbles per ml with a number mean diameter of 3.6 μm . This suspension was frozen at -18° and left at this temperature overnight. The day after the suspension was thawed at room temperature. The suspension analysed before and after freeze/thawing had the following characteristics:

TABLE 6

Sample (with air)	Absorbance 700 nm	Bubble conc. ($\times 10^8/\text{ml}$)	Diameter Dn (μm)
native	0.25	1.4	3.6
after freeze/thaw	0.13	0.4	6.3

The results in Table 6 show certain degree of destruction of the air containing microbubbles by freezing and defrosting cycle. When instead of pure air the albumin microbubbles are prepared with mixtures of air containing about 5% by vol. of C_5F_{12} or C_3F_8 , the stability of the

microspheres against freeze/thaw loss of bubble count was greatly improved (see Table 7). From the results obtained with albumin microspheres it can also be seen that freeze/thaw cycles in case of air microbubbles are detrimental for the lower end of sizes of the microbubble population i.e. that the microbubbles with average size of about 5 μm or more have better resistance and chance of survival than the smaller microbubbles.

TABLE 7

Sample (air + 5% C ₅ F ₁₂)	Absorbance 700 nm	Bubble conc ($\times 10^8/\text{ml}$)	Diameter Dn (μm)
native	0.64	2.4	3.7
after freeze/thaw	0.39	1.1	4.3

10

Example 8

When 3 g of saccharide microparticles SHU-454, a commercial echo contrast agent (Echovist®, Schering, Germany) were reconstituted in a galactose solution (8.5 ml, 200 mg/ml) as recommended by the manufacturer and submitted to a freeze/thaw treatment, only few bubbles were present in the solution after thawing. If 10 mg per ml of a mixture of dipalmitoylphosphatidylglycerol and Pluronic® F₆₈ (1:5, w:w) were added to the galactose solution prior to the addition of the saccharide microparticles, stable microbubbles could be obtained at a concentration of 2.5×10^8 bubbles per ml. After freezing and thawing the bubble concentration dropped, about three orders of magnitude, to 2.3×10^5 per ml indicating a considerable loss of microbubbles during the treatment. However if prior to reconstitution, air in the gas phase was replaced by a mixture of air containing 10% C₅F₁₂, the bubbles were more stable and also more resistant to a freeze/thaw treatment. The loss of microbubbles in the later case was only 2.3×10^8 as the concentration dropped from 3.9×10^8 to 1.6×10^8 bubbles per ml.

30

Example 9

Polymeric microballoons were prepared using the technique described in Example 4 of EP-A-0 458 745 (Bracco International). The polymer used in this preparation was poly-POMEG which is described in US 4'888'398. The microballoons were suspended at a concentration of 1.8×10^8 particles per ml in distilled water, 0.9% NaCl, 5% dextrose, and 3% glycerol. Each of these suspensions was frozen then thawed. No detectable change was observed after thawing, neither on the total particle concentration, nor on the mean particle diameter.

Example 10

A quantity of 126 mg of egg lecithin and 27 mg of cholesterol were dissolved in 9 ml of diethylether in a 200 ml round bottom flask. To the solution were added 3 ml of 0.2 molar aqueous solution of sodium bicarbonate with ionophore A23187 and the resulting two phase system sonicated until becoming homogeneous. The mixture was evaporated to dryness on a Rotavapor and a 3 ml of a 0.2 molar aqueous bicarbonate solution were added to the flask containing the lipid deposit.

After standing for a while, the resulting liposome suspension was dialysed against saline to eliminate non-entrapped bicarbonate and acidified. After a while it was washed with distilled water and then passed several times through a cascade of carbonate filters. An aliquot of the suspension of liposomes with size below $50 \mu\text{m}$ was then frozen at -18° and stored at this temperature. Two weeks later the suspension was thawed at room temperature. The suspension analysed before and after freeze/thawing showed an acceptably low loss of echogenicity and microbubble count.

Example 11

Procedure of the Example 3 was repeated using SF_6 and air containing 5% C_5F_{12} as the gas phase and the samples of the resulting suspension were frozen at -18°C , -45°C , -76°C and -196°C . After thirty days

of storage at the corresponding freezing temperatures the samples were defrosted and suspensions analysed. The results obtained are presented in Table 8. The concentration of microbubbles in the samples before freezing was $11.6 \times 10^7/\text{ml}$ for SF_6 and $9.8 \times 10^7/\text{ml}$ for the air/5% C_5F_{12} mixture while the respective volumes of gases in the samples prior to storing were 2.9 $\mu\text{l}/\text{ml}$ and 5.9 $\mu\text{l}/\text{ml}$. The average microbubble diameter for the two gases was 2.3 μm and 4.2 μm .

From the results it follows that the lower the temperature of storage the greater loss in the microbubble concentration and the total amount of gas recovered upon defrosting. The results further show that for defrosted samples of suspensions with SF_6 the average diameter at first increases and then as the temperature is lowered sharply decreases. For the air/5% C_5F_{12} mixture there is a relatively small change in the microbubble diameter. Results also show that the average microbubble diameter decreases with decrease in the storage temperature. As shown in Fig. 1 for suspensions with SF_6 and air/ C_5F_{12} mixture only 51.7% and 52% of the initial microbubble population is recovered after storage at -196°C . However, as seen from Fig. 2 the total gas volume recovered after the storage for SF_6 is 21.1% of the initial volume while for air/ C_5F_{12} mixture the volume recovered is 46.5%. This indicates that the the size of microbubbles in the case of suspensions prepared with SF_6 has changed, i.e. that the microbubbles recovered have reduced diameters.

TABLE 8

Gas	Gas volume recov. $\mu\text{l}/\text{ml}$	Diam Dn after thaw	Bubble conc. $\times 10^7$ recov	Temp. $^\circ\text{C}$	Gas mixture air with 5% C_5F_{12}	Gas volume recov. $\mu\text{l}/\text{ml}$	Diam Dn after thaw	Bubble conc. $\times 10^7$ recov
SF_6	2.3	2.4	10.0	-18	air/ C_5F_{12}	5.5	4.6	7.7
SF_6	2.8	2.6	7.9	-45	air/ C_5F_{12}	4.2	4.5	6.2
SF_6	1.8	2.5	6.7	-70	air/ C_5F_{12}	3.9	4.4	5.6
SF_6	0.6	2.0	6.0	-196	air/ C_5F_{12}	2.7	4.0	5.1

Fig. 3 and 4 illustrate the effect of freezing or storage temperature on the resistance to pressure change of suspensions of microbubbles

containing a mixture of air with 5% C₅F₁₂. In the diagram in Fig. 3 absorbance (measured at 700 nm) is presented as a function of pressure applied onto suspensions after storage for three days at different temperatures. From this diagram it follows that the decrease in the storage
5 temperature has an impact on the properties of the suspensions such that the change in properties of the suspensions stored at temperatures between -18°C and -76°C is significant while the change for the samples stored between -76°C and -196°C is relatively small. Thus maintaining storage temperatures below -76°C does not seem to provide further
10 advantages. In view of the costs involved choosing temperatures below -76°C may be justified only in exceptional cases.

Fig. 4 on the other hand shows that if suspensions of microbubbles containing air/5% of C₅F₁₂ mixture are stored for three days at low
15 temperatures their resistance to pressure variation remains relatively unchanged while the same suspension kept during the same period at 25°C loses about 10% of its initial resistance to pressure variations.

The exact procedure and importance of critical pressure and the
20 absorbance measurement has already been explained in EP-A-0 554 213 incorporated herein by reference.

Example 12

25 Two-dimensional echocardiography was performed using an ACUSON 128 XP 5 equipment (Acuson Corp. USA) with the preparations of Example 1, 3 and 7 in experimental minipigs following peripheral vein injection of 0.04 ml/kg body weight. Left ventricle echo contrast
30 enhancement was assessed in the case of native as well as frozen/thawed samples. No significant differences were noticed even in the cases of samples such as the ones described in Example 7 for albumin microspheres, indicating that the residual bubbles were largely sufficient to produce a strong and long lasting echo enhancement.

Claims

1. A frozen suspension of gas bubbles immobilised within a frozen
5 aqueous carrier medium, characterised in that the carrier medium
comprising the gas bubbles and usual additives is a physiologically
acceptable carrier, the immobilised gas bubbles are microbubbles bounded
by an evanescent envelope or a tangible membrane, the suspension, when
10 in liquid form, being injectable and useful as a contrast agent in ultrasonic
imaging of blood pool and tissue of living beings.

2. The suspension of claim 1, wherein the temperature of the
frozen medium is between -1°C and -196°C, preferably between -10°C and
-76°C.
15

3. The suspension of claim 1 or 2, wherein the size of most of the
microbubbles is below 50 µm, preferably below 10 µm.

4. The suspension of claim 3, wherein the size of the microbubbles
20 is between 2 µm and 9 µm, preferably between 3 µm and 5 µm.

5. The suspension of claim 1 or 2, wherein the additives include, as
surfactants, lamellar phospholipids in the form of mono- or pluri-
molecular membrane layers.
25

6. The suspension of claim 5, wherein the lamellar phospholipids
are in the form of unilamellar or multilamellar liposomes.

7. The suspension of claim 5, wherein the lamellar phospholipids
30 are saturated phospholipids.

8. The suspension of claim 6 or 7, wherein the phospholipids are
selected from phosphatidic acid, phosphatidylcholine, phosphatidyl-
ethanolamine, phosphatidylserine, phosphatidylglycerol, phosphatidyl-
35 inositol, cardiolipin and sphingomyelin or mixtures thereof.

9. The suspension of claim 1 or 2, wherein the additives include
substances selected from dicetylphosphate, cholesterol, ergosterol,

phytosterol, sitosterol, lanosterol, tocopherol, propyl gallate, ascorbyl palmitate and butylated hydroxytoluene.

10. The suspension of claim 1 or 2, wherein the additives include
5 sorbitol or non-ionic surfactants such as polyoxyethylene/polyoxypropylene copolymers.

11. The suspension of any of preceding claims, wherein the
10 additives include viscosity enhancers and/or stabilisers selected from linear and cross-linked poly- and oligo-saccharides, sugars, hydrophilic polymers and iodinated compounds in a weight ratio to the surfactants comprised between about 1:5 and 100:1.

12. The suspension of any of preceding claims, wherein the
15 additives further comprise up to 50% by weight of non-laminar surfactants selected from fatty acids, esters and ethers of fatty acids and alcohols with polyols.

13. The suspension of claim 12, wherein the polyols are
20 polyalkylene glycols, polyalkylenated sugars and other carbohydrates, and poly-alkylenated glycerol.

14. The suspension of claim 1 or 2, containing 10^7 - 10^8
25 microbubbles/ml, 10^8 - 10^9 microbubbles/ml or 10^9 - 10^{10} microbubbles/ml.

15. The suspension of claim 1 or 2, wherein the membrane is made
of synthetic or natural polymer or protein.

16. The suspension of claim 15, wherein the polymer is selected
30 from polysaccharides, polyamino acids and their esters, polylactides and polyglycolides and their copolymers, copolymers of lactides and lactones, polypeptides, poly-(ortho)esters, polydioxanone, poly- β -aminoketones, polyphosphazenes, polyanhydrides, polyalkyl-(cyano)-acrylates,
35 polyolefins, polyacrylates, polyacrylonitrile, non-hydrolyzable polyesters, polyurethanes and poly-ureas, polyglutamic or polyaspartic acid derivatives and their copolymers with other amino acids.

17. The suspension of claim 15, wherein the protein is albumin.

18. The suspension of claim 1, wherein the gas is selected from halogen containing gases, air, oxygen, nitrogen, carbon dioxide or mixtures thereof.

19. The suspension of claim 18, wherein the halogen-containing gas is selected from the group consisting of SF₆, CF₄, C₂F₆, C₂F₈, C₃F₆, C₃F₈, C₄F₆, C₄F₈, C₄F₁₀, C₅F₁₀, C₅F₁₂ and mixtures thereof.

20. A method of storing microbubble suspensions according to claims 1-19, characterised by the steps of:

- a) placing the liquid suspension into a cooling device,
- b) immobilising the microbubbles by cooling to a temperature below the freezing point of the suspension, preferably a temperature between -1°C and -196°C, and more preferably a temperature between -10°C and -76°C and,
- c) maintaining the freezing conditions for prolonged periods of time.

21. The method of claim 20, wherein the frozen suspension is kept in an atmosphere of an inert gas or a mixture of gases at least one of which is the gas encapsulated in the microbubbles.

22. The method of claim 20, wherein the microbubbles contain gas or mixture of gases at least one of which has a boiling point below -18°C.

23. The method of claim 20, wherein prior to its use the suspension is defrosted and maintained at room temperature for a period of time.

24. Injectable suspensions of claims 1-19 for use in ultrasonic imaging of organs and tissue.

25. Use of injectable suspensions of claims 1-19 for the manufacture of ultrasound echographic contrast agents.




Figure 1




Figure 2

3 / 6




Figure 3




Figure 4

SUBSTITUTE SHEET (RULE 26)




Figure 5A




Figure 5B

6 / 6




Figure 6A




Figure 6B

SUBSTITUTE SHEET (RULE 26)

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/IB 95/01124

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 A61K49/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,4 347 707 (VALERY B. ZEMELMAN) 7 September 1982 cited in the application see claims ---	1-25
A	DE,A,14 67 900 (FERRING AB.) 16 January 1969 see the whole document ---	1-25
A	J. LIPOSOME RES., vol. 4, no. 2, pages 861-874, UNGER EVAN ET AL. 'GAS FILLED LIPID BILAYERS AS IMAGING CONTRAST AGENTS.' see the whole document -----	5-9,24, 25

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

11 March 1996

Date of mailing of the international search report

02. 04. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Berte, M

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No.

PCT/IB 95/01124

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4347707	07-09-82	NONE	
DE-A-1467900	16-01-69	NONE	

THIS PAGE BLANK (USPTO)